

# HX Production Group Limited

HK Address: Unit 11D, Tak Wing Ind Bldg, 3 Tsun Wen Rd, Hong Kong CN Address: 14 Qunhua Road, West Circle Road, Jiangmen, GD, China Tel: (86) 188 252 16380/ (852) 3525 1553 ; Fax: (852) 3525 1559

## Material Data Sheet

## **PC Film/Sheet Products**

#### 产品描述 Description:

#### HLPC: Long Hairline/Gloss or Shredded Hairline/Gloss

**HLPC** is a Hairline structured film with minor anti-scratches function. Processed under UV coating, the long hairline appears as a metallic surface which is commonly used for fascial panel for electronic white goods appliance as well as mobile products. It can be used for printing, silk screen-printing, thermoforming, IMD, etc.

**HLPC** can be available for hairline structure with both **Soft** type (no touch feeling) and **standard** type (with stronger indentation touch feeling) as well as shredded or Long Hairline.

### 物性表 Typical Property Table

特性	测试方法	单位	测试值
Property	Test Method	Units	Test value
物理性 PHYSICAL			
比重 Specific Gravity	ASTM D792	g/cm <sup>3</sup>	1.2
透光率 Light Transmissivity	ASTM D1003	%	85~90
雾度 Haze	ASTM D1003	%	< 55 ~ 65
平均吸水率 Water Absorption Equilibrium, 24 hrs	ASTM D570	%	0.23
机械性 MECHANICAL			
拉伸强度 Tensile Strength	ASTM D882	psi	8,800
	ISOR1184-1987	MPa	60
极限延伸率 Elongation at break	ASTM D882	%	>90
冲击强度 Impact Strength @ 10mils	JIS-K6745	In-lbs	120
耐温性 THERMAL			
维卡软化点 Vicat Softening Point 120 °C/hr, 10N load	ISO 306	°C	151
电气性 ELECTRICAL			
介电强度 Dielectric Strength (@ 10mils)	ASTM D149	V/mil	1,700
体积绝缘 Volume Resistivity@25°C,50%RH	ASTM D257	Ω.cm	10 <sup>16</sup>
表面绝缘 Surface Resistivity@25°C,50%RH	ASTM D257	Ω	1015
阻燃性 FLAMMABILITY			
UL 防火等级 UL Flammability @≥10 mils	UL Measure (SGS)	UL94	V-2
厚度公差 Thickness tolerance <0.250mm(0.010")		%	±10%
≥0.250mm(0.010")			$\pm 5\%$

Note: The values in the typical property table are for reference only. For further requirements, please contact us.